



CAB-O-SIL® HS-5

CAB-O-SIL HS-5 is a high surface fumed silica which imparts significant increase in viscosity in liquid systems and in reinforcement of sealants and rubbers.

All untreated fumed silicas are characterized by:

- High purity
- Aggregated structure
- Submicron particle size
- Low bulk density
- Hydrophilic surface

Application Information:

Rheology Control for Coatings, Adhesive and other Liquid Systems:

CAB-O-SIL HS-5 can be used to provide thickening, thixotropic (shear-thinning), and anti-settling behavior in liquid systems. High shear dispersion equipment is required to realize the full benefits of HS-5. For clear coatings and other systems, very well dispersed HS-5 provides good transparency.

CAB-O-SIL HS-5 is most efficient in non-polar to medium polar systems. For more polar systems, treated fumed silicas are more efficient.

Reinforcement of Silicone and Organic Rubber:

CAB-O-SIL HS-5 can be used for reinforcement of silicone rubber and can be used to reinforce organic rubbers. It imparts good increase in hardness, tensile and elongation.

Packaging Options:

CAB-O-SIL HS-5 is packaged in multi-wall Kraft paper bags and flexible intermediate bulk containers (FIBCs). It is available in poly-shrouded units containing 18 x 10 lb. paper bags (180 lb. net weight) and in 250 lb. FIBCs.

Product Sales Specifications:

Sales specifications for this product may be obtained by contacting a sales or technical service manager at the Cabot Corporation office in your region.

Material Safety Data Sheet:

A Material Safety Data Sheet for this product may be obtained by contacting the Cabot Corporation office in your region or can be downloaded from our website: www.cabot-corp.com

This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. Cabot disclaims all warranties express or implied, including merchantability or fitness for a particular purpose as to (i) such information, (ii) any product or (iii) intellectual property infringement. In no event is Cabot responsible for, and Cabot does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.

NORTH AMERICA	EUROPE	ASIA/ PACIFIC	SOUTH AMERICA	CHINA
Cabot Corporation Business and Technical Center 157 Concord Road Billerica, MA 01821-7001 USA Customer Service: Phone: (800) 526-7591 Technical Service: Phone: +1 (978) 663-3455 Phone: (800) 462-2313 Fax: +1 (978) 670-6167	Cabot Interleuvenlaan 15 I B-3001 Leuven BELGIUM Tel: +32 16 39 24 00 Fax: +32 16 39 24 44	Cabot Specialty Chemicals Level 21 MNI Tower 2 11, Jalan Pinang 50450 Kuala Lumpur MALAYSIA Phone: +60 3 2164 8352 Fax: +60 3 2161 0253	Cabot Latin America Division Rua do Paraíso, 148 - 5º andar CEP 04103-000, São Paulo SP BRAZIL Customer Service: Phone: +55 11 2144 6400 Fax: +55 11 3253 0051	Cabot (China) Limited 558 Shuangbai Lu Wujing Shanghai 201108 CHINA Phone: +86 21 5175 8800 Fax: +86 21 6434 5532